

Fiche technique Carbure

Désignation ISO	Composition (%)		Grosseur grains (μm)	Dureté (HV30)
	WC	Co		
K20-K30	90	10	0.5-0.9	1600
K10-K20	92	8	0.2-0.5	1930
K40 UF	90	10	0.5-0.7	1610