

Fiche technique Aciers

Acier	US	Composition (%)							
		C	Si	Mn	Cr	W	Mo	V	Co
HSS	M2	0,90	0,20	0,30	4,20	6,45	4,98	1,90	
HSSCo5	M35	0,92	0,30	0,20	3,98	6,45	5,18	1,85	4,56
HSS Co8	M42	1,08			4,00	1,50	9,50	1,15	8,00
HSS E	M3	1,22			4,15	6,45	4,95	2,95	